

BISCOM INTERNATIONAL AG

*Aquasanastrasse 8
CH- 7001 Chur
Switzerland
Tel. +41 81 252 70 96
Fax +41 81 252 70 98*

Technical Data Sheet

Edition Sept 2009

Copper Powder less 500 µm

Material: Copper Magnesium Powder, Water Atomised, Irregular

Application: Friction Pads

Inspection Characteristic

Sieve analysis ISO 4497 cumulative:	Unit	Lower Limit value	Upper Limit value
-------------------------------------	------	-------------------	-------------------

➤ 1000 µm	%	-	0,0
➤ 500 µm	%	-	1,0
➤ 250 µm	%	10	50
➤ 125 µm	%	70	95
➤ 63 µm	%	95	100

Apparent density ISO 3923/1	g/cm3	2,7	4
-----------------------------	-------	-----	---

Chemical analysis:

Copper (Cu)	%	99	-
-------------	---	----	---

All statements, technical information and recommendations herein are based on tests and data, which our Company believes to be currently reliable. The accuracy of completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto. Product characteristics may change due to technical development and /or improvement of production methods